


Control Joints / Expansion Joints VS Series - PVC Control Joint



TEST DATA

	<u>Iypical Values</u>	<u>lest Method</u>
Tensile Strength	2200	ASTM D-412
Ultimate Elongation	350	ASTM D-412
Shore A Hardness	85	ASTM D-2240
Low Temp Brittleness	-35	ASTM D-746

IMPORTANT: Since each construction project is unique, the appropriate selection and use of any product contained herein must be determined by competent architects, engineers and other appropriate professionals who are familiar with the specific requirements of the project in question. This drawing and/or data sheet is the confidential and proprietary information of Hohmann & Barnard, Inc. and is not to be reproduced, copied or disclosed, in whole or in part, without the prior written consent of H&B.

VS-1118